

**TEST REPORT**

DATE: 11-13-2019

Page 1 of 1

TEST NUMBER: 0262057

<b>CLIENT</b>	
<b>TEST METHOD CONDUCTED</b>	ASTM F925 (Regular) Standard Test Method for Resistance to Chemicals of Resilient Flooring
<b>DESCRIPTION OF TEST SAMPLE</b>	
<b>IDENTIFICATION</b>	With Shielded Grouted Line
<b>CONSTRUCTION</b>	SPC Vinyl Tiles

**TEST RESULTS**

	5 MINUTE RATINGS			24 HOUR RATINGS		
STAINING AGENT	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE	SURFACE DULLING	SURFACE ATTACK	COLOR CHANGE
White Vinegar 5% Acetic Acid AR	0	0	0	0	0	0
Rubbing Alcohol 70% Isopropyl Alcohol	0	0	0	0	0	0
White Mineral Oil Medicinal grade	0	0	0	0	0	0
NaOH Solution 5% AR	0	0	0	0	0	0
HCl Solution 5% AR	0	0	0	0	0	0
H2SO Solution 5% AR	0	0	0	0	0	0
Household Ammonia Solution 5% NH4OH AR	0	0	0	0	0	0
Household Bleach 5.25% NaClO AR	0	0	0	0	0	0
Disinfectant - Phenol Type 5% Active Phenol	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Olive Oil	0	0	0	0	0	0
Unleaded Gasoline	0	0	0	0	0	0

**RATING KEY**

- 0 - No change (----)
- 1 - Slight change
- 2 - Moderate change
- 3 - Severe change

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.